





Polyester Coating System Technical Data

Areco's Polyester coating system on a base of polyester resin is the most economical system when a corrosivity category of C1-C3 is required. The coating system exhibits very good properties outdoors and a balance between flexibility and hardness/surface durability. The coating has a very good gloss and colour stability, as well as excellent resistance to metal blackening and good corrosion protection. Polyester coating system has 10 years quality warranty, see specific document, Areco WARRANTY.

Base material	Continuously hot-dip g	galvanised sheet steel according to EN10346.		
Coating system	Visible side:	25 μm (incl. primary layer 5 μm)		
	Reverse side:	7-10 µm Reverse side varnish		
	Properties	Test method	Data/value	
	Paint thickness:	EN 13523-1	see above	
	Gloss:	EN 13523-2	30 – 50	
	Bendability, radius:	EN 13523-7	3T	
	(T-bend)			
	Impact resistance:	EN 13523-12	20N	
Temperature resistance	90 °C			
Resistance to chemicals	Acids	Resistant		
	Bases	Resistant		
	Aliphatics	Resistant		
	Aromatic compounds	Resistant		
	Alcohols	Resistant		
	Ketones	Not durable		
	Chlorinated	Limited durability		
	Mineral oils	Resistant		
Reaction to fire	A1 according to EN 13501-1			
Anti-slip	Properties corresponding to other strip-coated sheet metal materials			
Corrosion category	RC3			
UV category	Ruv3			

